



NovoColor® HP II

Low VOC Water-Only Colorant Technical Data Sheet

PRODUCT NUMBER	MASS-TONE	TINT	PRODUCT CODE	COLORANT NAME	CI PIGMENT NAME	TYPICAL PROPERTIES						
						DENSITY		% PRIME PIGMENT BY WT.	% INERT PIGMENT BY WT.	% TOTAL SOLIDS BY WT.	Theoretical VOC (g/L)	% WATER BY WEIGHT
lbs/gal	g/cc											
8600N			KX	White	PW 6	16.9	2.0	56.4	9.4	73.8	0.0	26.2
8613N			AX	Yellow	Blend	10.7	1.3	24.7	7.7	42.1	0.0	57.8
8614N			T	Medium Yellow	Blend	10.0	1.2	20.5	13.0	44.2	0.0	55.8
8621N			DU	Phthalo Green	PG 7	11.2	1.3	13.6	27.0	52.6	0.0	47.5
8632N			EU	Phthalo Blue	PB 15:2	10.5	1.3	9.6	26.3	46.9	0.0	53.1
8635N			F	Red Oxide	Blend	17.0	2.0	60.8	3.1	73.0	0.0	27.0
8647N			R	Red	Blend	11.6	1.4	10.9	32.1	51.5	0.0	48.5
8649N			V	Magenta	PR 122	10.5	1.3	12.2	24.7	49.5	0.0	50.5
8651N			RU	High Hide Red	Blend	12.3	1.5	20.7	31.4	64.7	0.0	35.3
8678N			C	Yellow Oxide	PY 42	14.7	1.8	54.2	1.6	67.2	0.0	32.8
8688N			L	Raw Umber	PB 7	11.3	1.4	21.9	13.7	52.7	0.0	47.3
8691N			B	Lamp Black	PBk 7	11.5	1.4	8.1	29.7	46.2	0.0	53.8
8697N			I	Brown Oxide	Blend	13.0	1.6	37.0	9.1	55.2	0.0	44.8

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. CCA assumes no obligation or liability for use of this information. **UNLESS CCA AGREES OTHERWISE IN WRITING, CCA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. CCA WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.