

EPS[®] 2128

ACRYLIC EMULSION

DATA SHEET

Description

EPS 2128 is an acrylic emulsion for use in removable pressure sensitive applications. EPS 2128 exhibits low peel, low tack, and high shear values.

- ✓ 180 Peel (PSTC-101) 1.9 lbs/in
- ✓ Polyken Probe (ASTM D2979) 82 g/cm²
- ✓ Static Shear (PSTC-107)* >10,000 minutes (1"x1"x1kg)

Tentative or Typical Properties

Weight Solids*: 52.5 ± 1.0%

Volume Solids 51 +/- 0.70%

Weight/Gallon*: 8.60 ± 0.10

Tg (measured): -22°C

pH: 7.0 to 9.0

Viscosity (#2 @20 rpm): N/A

Acid Value (on solids): N/A

Flash Point: >212 °F

Suggested Formulations

none

*Product specification

rev 12 May 2011

Questions? Call EPS Technical Service @ 1-800-601-8111

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. **UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.