

EPS[®] 2130 ACRYLIC EMULSION

DATA SHEET

Description

EPS 2130 is an acrylic emulsion for use in removable pressure sensitive applications. EPS 2130 exhibits low peel, moderate tack, and high shear values.

- ✓ 90° Peel (PSTC-101) 9.0 oz/in
- ✓ Polyken Probe (ASTM D2979) 262 g/cm²
- ✓ Static Shear (PSTC-107)* >10,000 minutes (1"x1"x1kg)

Tentative or Typical Properties

*Weight Solids**: 57.0 ± 1.0%
Volume Solids 56.3 +/- 0.70%
*Weight/Gallon**: 8.65 ± 0.10
Tg (theoretical): -45°C
pH: 8.0-10.0

Suggested Formulations

none

Flash Point: >212 °F

*Product specification

rev 7 June 2019

Questions? Call EPS Technical Service @ 1-800-601-8111

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. **UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.