

PC-Mull[®] VP 209 TECHNISCHES MERKBLATT

Beschreibung

PC-Mull[®] VP 209 ist eine selbstvernetzende Acrylatcopolymerdispersion in Wasser für die Holzbeschichtung.

Eigenschaften

PC-Mull[®] VP 209 wird für wässrige Holz- und Parkettbeschichtungen mit hervorragender Anfeuerung eingesetzt, die der DIN 68861-1B entsprechen.

Physikalische daten

Aussehen:	bräunlich
Festkörper [%]:	42,0 ± 1
Viskosität, 23 °C [mPa.s]: (Brookfield, Spindle 2)	< 500
pH-wert [-]:	8,0 – 9,0

Typische daten

MFFT [°C]:	+13
Dichte @ 20 °C [kg/m ³]:	1054

Lagerung

PC-Mull[®] VP 209 sollte in einem geschlossenen Behälter an einem trockenen Ort bei Lagertemperaturen zwischen 5 °C and 30 °C gespeichert werden.

Lagerstabilität

Unter der oben genannten Lagerbedingungen ist die Stabilität 6 Monate ab Werk.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. **UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.