

EPS[®] 4627

URTHANE MODIFIED ALKYD

DATA SHEET

Description

EPS 4627 is a urethane modified alkyd designed to provide very fast dry with fast hardness development. This balance of properties makes EPS 4627 an excellent choice for gloss and satin varnishes and as a modifier for porch and deck enamels.

- ✓ Fast dry
- ✓ Improved hardness development
- ✓ Excellent blending vehicle for low VOC finishes

Specifications

Weight Solids: 60.0 ± 0.7%
 Weight/Gallon: 7.66 ± 0.10
 Viscosity: U – V
 Acid Value: 3 Max
 Color: 6 Max

Suggested Drier Package

(% Metal on Resin Solids)

Manganese	0.01 – 0.02
Active-8	0.10 – 0.30

Typical Properties

Volume Solids: 53.2 ± 0.7%
 Oil Type: Mixed
 Visc. (Reduced): N/A
 Modifier: TDI
 Solvent: LAMS/Aromatic 100
 (37.3%/2.7%)

Suggested Formulations

None

05-09-2014

Questions? Call EPS Technical Service @ 1-800-601-8111

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. **UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option