

EPS[®] 4681

URETHANE MODIFIED ALKYD

DATA SHEET

Description

EPS 4681 is a urethane modified alkyd designed to provide fast dry, early hardness development, light color and good flattening efficiency. This balance of properties makes EPS 4681 an excellent choice for gloss and satin varnishes and as a modifier for trade sales enamels.

- ✓ Fast dry
- ✓ Less yellowing

Specifications

Weight Solids: 50.0 ± 0.7%
Weight/Gallon: 7.48 ± 0.10
Viscosity: Y – Z1
Acid Value: 2 Max
Color: 4 Max

Suggested Drier Package

(% Metal on Resin Solids)

Manganese 0.01 – 0.02
Active-8 0.10 – 0.20

Typical Properties

Volume Solids: 42.4 ± 0.7%
Oil Type: Soya
Visc. (Reduced): N – P @ 45%
Modifier: TDI
Solvent: LAMS/Aromatic 100
(47.8%/2.2%)

Suggested Formulations

None

05-09-2014

Questions? Call EPS Technical Service @ 1-800-601-8111

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. **UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option