

# EPS<sup>®</sup> 533

# DATA SHEET

## Description

EPS<sup>®</sup> 533 is a versatile, acrylic polymer in water, offering outstanding tannin and stain blocking characteristics, with excellent adhesion to multiple substrates, early water resistance and low water uptake.

## Properties

EPS<sup>®</sup> 533 is a binder developed for primer and topcoat applications on wood with excellent exterior durability.

## Physical data

Solids by weight [%]:	45.5 ± 1
Viscosity, 23 °C [mPa·s]: (Brookfield, Spindle 2)	< 500
pH value [-]:	7.0 – 8.0

## Typical values

MFFT [°C]:	+ 9
Density @ 20 °C [kg/m <sup>3</sup> ]:	1033

## Storage

EPS<sup>®</sup> 533 should be stored in a closed container at a dry place at storage temperatures between 5 °C and 30 °C.

## Stability

Under the above mentioned storage condition the stability will be 12 months ex works.