

EPS® 6514 MEDIUM OIL ALKYD

DATA SHEET

Description

EPS 6514 is a medium oil alkyd. EPS 6514 is designed to provide high gloss, pigment wetting and excellent flow and leveling. This balance of properties makes EPS 6514 an excellent choice for industrial maintenance and architectural coatings. This product is xylene non-reportable.

<u>Specifications</u> <u>Suggested Drier Package</u>

Weight Solids: 50.0 ± 0.7% (% Metal on Resin Solids)

Calcium 0.05

Weight/Gallon: 7.50 ± 0.10 Cobalt 0.03

Viscosity: Z1 -Z3 Manganese 0.05

Acid Value*: 5 - 10 Zirconium 0.30

Color: 2 - 7

<u>Typical Properties</u> <u>Suggested Formulations</u>

Volume Solids: 42.5 ± 0.7% None

Oil Type: Soya

Visc. (Reduced): J-L@ 40% in LAMS

OH Value: 48 (theoretical)

Modifier: None

Solvent Composition: LAMS/Aromatic 100

48.4%/1.6%

*Acid value on solids

05-09-2014

Questions? Call EPS Technical Service @ 1-800-601-8111

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option