www.eps-materials.com



# EPS<sup>®</sup> 6684 LONG OIL ALKYD



## **Description**

**EPS 6684** is a long oil alkyd. EPS 6684 is designed to provide excellent flow, leveling and durability. This balance of properties makes EPS 6684 an excellent choice for architectural enamels and industrial maintenance paints.

- Excellent flow and leveling
- ✓ Excellent pigment wetting
- ✓ Fast dry
- ✓ Excellent adhesion

#### **Specifications**

Weight Solids:	$60.0 \pm 0.7\%$
Weight/Gallon:	7.70 ± 0.10
Viscosity:	$Y - Z_1$
Acid Value*:	10 max
Color:	7 max

#### Typical Properties

Volume Solids: 52.3 ± 0.7% Oil Type: Soya Modifier: None Solvent Composition: LAMS/Xylene (38.1/1.9) OH Value: 58 (theoretical)

\*Acid value on solids

Suggested Drier Pac	kage
(% Metal on Resin Solids)	
Cobalt	0.07
Calcium	0.05
Zirconium	0.40

Suggested Formulation

None

05-09-2014

### Questions? Call EPS Technical Service @ 1-800-601-8111

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option