

EPS[®] 7506

SOLUTION ACRYLIC RESIN

DATA SHEET

Description

EPS 7506 is a solution acrylic resin in an aromatic naphtha and tertiary-butyl acetate (TBAC) blend. It can be further formulated with exempt solvents for concrete cure and seal applications at lower VOC. When properly formulated to 25% solids, EPS 7506 is designed to meet the requirements of ASTM C-1315, Type I, Class C.

- ✓ Excellent water resistance
- ✓ High gloss
- ✓ Excellent water retention properties

Specifications

Weight Solids: 50.0 ± 0.7%

Weight/Gallon: 7.94 ± 0.1 lbs./Gal.

Viscosity: Z1 – Z₃

Color: 1 max

Typical Properties

Volume Solids: 44.5 ± 0.7%

Acid Value: N/A

Solvent Composition: TBAC / A-150
(28%/ 22%)

05-09-2014

Questions? Call EPS Technical Service @ 1-800-601-8111

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. **UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option