

EPS BV P.O. Box 358, 3340 AJ H.I.Ambacht Nijverheidsweg 35, 3341 LJ H.I.Ambacht The Netherlands T : +31 78 6833250 F : +31 78 6812697 info.nl@eps-materials.com

DYFLEX[®] LP 2945

DATA SHEET

Description

DYFLEX[®] LP 2945 is a pure acrylic copolymer in water.

Properties

DYFLEX[®] LP 2945 is a binder for in- and exterior applications with exceptional levelling properties, in-can transparency, excellent block- and superior water resistance. Primers based on DYFLEX[®] LP 2945 will pass the DUTCH BRL 0817 tests.

Physical data

Solids by weight [%]:	43.0 ± 1
Viscosity, 23 °C [mPa·s]:	< 500
(Brookfield, Spindle 2)	
pH value [-]:	7.5 – 8.5

Typical values

MFFT [°C]:	0
Density @ 20 °C [kg/m ³]:	1060

Storage

DYFLEX[®] LP 2945 should be stored in a closed container at a dry place at storage temperatures between 5 °C and 30 °C.

<u>Stability</u>

Under the above mentioned storage condition the stability will be 12 months ex works.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Date of issue: August 2019