

PC-Mull® 1015/1

DATA SHEET

Description

PC-Mull® 1015/1 is a pure acrylic copolymer dispersion and is used as a binder for high quality wood coatings.

Properties

PC-Mull® 1015/1 has outstanding mechanical and chemical resistance, combined with very good transparency and wood warming. Based on PC-Mull® 1015/1 coatings can be formulated, which correspond to the DIN 68861 1B. Compared to PC Mull® 1014, PC-Mull® 1015/1 shows better grain enhancement.

Physical data

Appearance:	slightly turbid
Solids by weight [%]:	40.0 ± 1.5
Viscosity, 23 °C [mPa·s]: (Brookfield, Spindle 2)	< 500
pH value [-]:	8.0 – 9.0

Typical values

MFFT [°C]:	+ 34
Density @ 20 °C [kg/m ³]:	1060

Storage

PC-Mull® 1015/1 should be stored in a closed container at a dry place at storage temperatures between 5 °C and 30 °C.

Stability

Under the above mentioned storage condition the stability will be 6 months ex works.