The Netherlands





PC-Mull[®] VP 433

DATA SHEET

Description

PC-Mull® VP 433 is a pure acrylic copolymer dispersion and is used as a binder for high quality wood coatings.

Properties

PC-Mull® VP 433 has outstanding mechanical and chemical resistance, combined with very good transparency and wood warming. Compared to PC-Mull[®] 1024, the PC-Mull[®] VP 433 is harder, shows a better block resistance and requires less solvent.

Physical data

Appearance: yellow-white

Solids by weight [%]: 45.0 ± 1

Viscosity, 23 °C [mPa·s]: < 500

(Brookfield, Spindle 2)

pH value [-]: 6.5 - 7.5

Typical values

+ 28 MFFT [°C]: Density @ 20 °C [kg/m³]: 1063

Storage

PC-Mull® VP 433 should be stored in a closed container at a dry place at storage temperatures between 5 °C and 30 °C.

Stability

Under the above mentioned storage condition the stability will be 6 months ex works.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Date of issue: December 2015